



Solar Control Low-e Glass
Pilkington **Solar-E™** Plus





Pilkington **Solar-E™** Plus solar control low-e

Glazing our way into the future

With all the benefits of a pyrolytic low-e, it's hard to imagine making it even better.

Pilkington has prevailed with its new line of Pilkington **Solar-E™** Plus glass products. Improvements to the low-e coating have given it the lowest solar heat gain coefficient (SHGC) of any pyrolytic family of products.

With a slightly deeper tint and improved solar performance, as noted by a lower SHGC, the Pilkington **Solar-E™** Plus tints are perfect for any new commercial building project or renovation. This new range of tints includes Grey, Blue-Green, EverGreen, Arctic Blue and our new natural tint, Graphite Blue.

This new coating offers low solar heat gain, lower reflectivity, and glare control, which all contribute to sustainable commercial construction.

Pilkington **Solar-E™** Plus can help earn LEED® or any other green building certification.

Sustainability credits can be achieved through improvements in proposed building performance ratings for new and renovated buildings.

Features and Benefits

- The low-e coating reduces the emissivity of glass and lowers the U-factor.
- Low SHGC values can result in significant savings in utility costs.
- Provides good visible light transmittance, helping to reduce the need for interior lighting.
- Low internal and external reflection, reducing uncomfortable glare from the sun and the need for blinds and shades.
- Low UV (ultraviolet) transmittance, reducing UV rays results in less fading.
- For further improved thermal control, add Pilkington **Energy Advantage™** low-e to an insulated unit (coating on the #4 surface).
- Can be laminated, toughened, bent and enameled using standard techniques.

Photos compliments of Intraco USA

Monolithic Performance Data^{1,10}

	Nominal Glass Thickness		Visible Light ²			Solar Energy ²			U-Factor ⁵			Solar Heat Gain Coefficient ⁷	Shading Coefficient ⁸
	in.	mm	Transmittance ³ %	Reflectance ⁴ %		Transmittance ³ %	Reflectance ⁴ %	UV Transmittance ² %	U.S. Summer [*]	U.S. Winter [*]	European ^{6**}		
				Outside	Inside								
Pilkington Solar-E™ Plus (coating on #2 surface)													
Grey	1/4	6	24	5	9	19	5	12	0.50	0.65	3.7	0.34	0.39
	5/16	8	19	5	8	15	5	9	0.50	0.65	3.7	0.31	0.36
Blue-Green	1/4	6	41	6	9	24	5	19	0.50	0.65	3.7	0.38	0.43
	5/16	8	39	6	9	21	5	15	0.50	0.65	3.7	0.35	0.41
EverGreen	1/4	6	38	6	9	17	5	8	0.50	0.65	3.7	0.32	0.37
	5/16	8	34	6	9	14	5	5	0.50	0.65	3.7	0.30	0.34
Arctic Blue	1/4	6	30	6	8	17	5	11	0.50	0.65	3.7	0.32	0.37
	5/16	8	27	6	8	14	5	9	0.50	0.65	3.7	0.30	0.35
Graphite Blue	1/4	6	28	5	8	24	5	21	0.50	0.65	3.7	0.39	0.44
	5/16	8	30	6	9	23	5	18	0.50	0.65	3.7	0.37	0.43

Insulating Glass Unit Performance Data^{1,10}

	Nominal Glass Thickness		Visible Light ²			Solar Energy ²			U-Factor ⁵						Solar Heat Gain Coefficient ⁷	Shading Coefficient ⁸
			Transmittance ³	Reflectance ⁴ %		Transmittance ³ %	Reflectance ⁴ %	UV Transmittance ² %	U.S. Summer*		U.S. Winter*		Europe**			
	in.	mm		Outside	Inside				Air	Argon	Air	Argon	Air	Argon		
Pilkington Solar-E™ Plus (coating on #2 surface) outer lite and Pilkington Optifloat™ Clear inner lite																
Grey	1/4	6	21	6	15	16	6	10	0.33	0.28	0.33	0.29	1.9	1.6	0.26	0.30
	5/16	8	17	6	14	12	5	7	0.33	0.28	0.33	0.29	1.8	1.5	0.23	0.26
Blue-Green	1/4	6	37	8	15	20	6	15	0.33	0.28	0.33	0.29	1.9	1.6	0.30	0.34
	5/16	8	34	7	15	17	6	12	0.33	0.28	0.33	0.29	1.8	1.5	0.27	0.31
EverGreen	1/4	6	34	8	15	15	6	7	0.33	0.28	0.33	0.29	1.9	1.6	0.24	0.28
	5/16	8	30	7	15	12	5	4	0.33	0.28	0.33	0.29	1.8	1.5	0.22	0.25
Arctic Blue	1/4	6	27	6	14	14	5	9	0.33	0.28	0.33	0.29	1.9	1.6	0.24	0.27
	5/16	8	24	6	14	12	5	7	0.33	0.28	0.33	0.29	1.8	1.5	0.22	0.25
Graphite Blue	1/4	6	25	6	14	19	5	16	0.33	0.28	0.33	0.29	1.9	1.6	0.30	0.34
	5/16	8	26	7	15	18	6	14	0.33	0.28	0.33	0.29	1.8	1.5	0.28	0.33
Pilkington Solar-E™ Plus (coating on #2 surface) outer lite and Pilkington Energy Advantage™ Low-e (coating on #3 surface) inner lite																
Grey	1/4	6	20	6	16	14	6	8	0.30	0.24	0.31	0.26	1.7	1.3	0.24	0.28
	5/16	8	16	6	15	11	5	5	0.30	0.24	0.31	0.26	1.7	1.3	0.21	0.24
Blue-Green	1/4	6	34	8	16	18	6	12	0.30	0.24	0.31	0.26	1.7	1.3	0.28	0.32
	5/16	8	32	8	16	15	6	9	0.30	0.24	0.31	0.26	1.7	1.3	0.25	0.29
EverGreen	1/4	6	31	8	16	13	6	5	0.30	0.24	0.31	0.26	1.7	1.3	0.23	0.26
	5/16	8	28	7	16	11	5	3	0.30	0.24	0.31	0.26	1.7	1.3	0.20	0.23
Arctic Blue	1/4	6	25	6	16	13	5	7	0.30	0.24	0.31	0.26	1.7	1.3	0.22	0.26
	5/16	8	22	6	15	11	5	5	0.30	0.24	0.31	0.26	1.7	1.3	0.20	0.23
Graphite Blue	1/4	6	23	6	16	17	6	13	0.30	0.24	0.31	0.26	1.7	1.3	0.28	0.32
	5/16	8	25	7	16	16	6	11	0.30	0.24	0.31	0.26	1.7	1.3	0.27	0.31
Pilkington Solar-E™ Plus (coating on #2 surface) outer lite and Pilkington Energy Advantage™ Low-e (coating on #4 surface) inner lite																
Grey	1/4	6	20	6	17	14	6	8	0.25	0.22	0.26	0.23	1.6	1.3	0.23	0.26
	5/16	8	16	6	16	11	5	5	0.24	0.22	0.26	0.23	1.6	1.3	0.20	0.23
Blue-Green	1/4	6	34	8	17	18	6	12	0.25	0.22	0.26	0.23	1.6	1.3	0.27	0.31
	5/16	8	32	7	16	15	6	9	0.24	0.22	0.26	0.23	1.6	1.3	0.24	0.28
EverGreen	1/4	6	31	8	17	13	6	5	0.25	0.22	0.26	0.23	1.6	1.3	0.22	0.25
	5/16	8	28	7	17	11	5	3	0.24	0.22	0.26	0.23	1.6	1.3	0.19	0.22
Arctic Blue	1/4	6	25	6	16	13	5	7	0.25	0.22	0.26	0.23	1.6	1.3	0.21	0.25
	5/16	8	22	6	16	11	5	5	0.24	0.22	0.26	0.23	1.6	1.3	0.19	0.22
Graphite Blue	1/4	6	23	6	16	17	6	13	0.25	0.22	0.26	0.23	1.6	1.3	0.27	0.31
	5/16	8	25	7	16	16	6	11	0.24	0.22	0.26	0.23	1.6	1.3	0.26	0.29

An insulating unit consists of two lites of equal glass thickness, and a 1/2 in. airspace.

*U.S. U-Factor (Btu/hr.sq ft. °F) is based on NFRC/ASTM standards, **European U-Factor (W/sq m K) is based on EN 410/673 (CEN) standard.

All performance values are center-of-glass values calculated using the LBNL Window 6.3 program. See Pilkington Architectural Product Guide for explanation of references - ^{1,10}.

Durability of the Coating

Pyrolytic coated glass can be handled, cut, tempered, bent and fabricated into insulating glass units using standard techniques. It has a virtually unlimited shelf-life and can be single glazed, inventoried locally and edge deletion is not required. Also, ceramic frit can be applied or silk screened to the coated surface and it will not oxidize or change color over time.

Applications

- Commercial buildings requiring solar control
- Low/mid/high rise buildings
- Medical/Hospital
- Educational facilities/Schools
- Office buildings
- Retail buildings



This publication provides only a general description of the product. Further, more detailed, information may be obtained from your local supplier of Pilkington products. It is the responsibility of the user to ensure that the use of this product is appropriate for any particular application and that such use complies with all relevant legislation, standards, codes of practice and other requirements. To the fullest extent permitted by applicable laws, Nippon Sheet Glass Co. Ltd. and its subsidiary companies disclaim all liability for any error in or omission from this publication and for all consequences of relying on it. Pilkington, "Optifloat," "Energy Advantage," and "Solar-E" are trademarks owned by Nippon Sheet Glass Co. Ltd, or a subsidiary thereof.



Pilkington North America

811 Madison Ave Toledo, Ohio 43604-5684

buildingproducts.pna@nsg.com

Tel 800 221 0444 • Fax 419 247 4573

www.pilkington.com/na